

# Sogni SK

## A modern and elegant system for decorating walls



*SOGNI SK is the modern and elegant professional system for decorating walls. The main feature of this translucent finish is the metallic or prismatic effect that changes tone according to the angle from which it is seen, giving a sleek glow to the wall surface. It is highly durable and washable thus suitable for all areas of your home and ideal for high traffic, public environments such as hotels, schools, hospitals and offices. A simple way to create special effects in vibrant colors that will result in a great sense of depth and texture.*



### Intended use:

Any normal, paintable interior or external wall surface, either Gypsum plaster based or rendered masonry.

### Surface treatment:

Ensure that the surface is clean, dry and free from peeling paint. In case of old and powdery walls or in presence of weak paint, apply a coat of ADIFIX primer thinned as specified and allow to dry. Apply one or two base coats of a prime quality, low absorption latex paint such as our TOPSAN Semigloss or FIRST.

### Preparation of the color:

Sogni SK is available in 9 pre-tinted Bases. To achieve the additional desired colors, add the specified quantity of Adicolor TINTER to either SK101 or SK102 Bases as indicated on the relative color chart.

### Application:

There are many possible ways of applying this product with a consequent different effect and resulting spread rate. The following are two examples of the method used to get the spread rate we quote.

**Stippled effect:** Starting from the top corner of the wall, apply Sogni SK by brush to an area of about 1 sq.m. at a time. Using either a rag stippler or a chamois pad, dipped and blotted to remove excess, immediately dab the wet product randomly, rotating continually your wrist to vary the pattern being created.

**Spatula effect:** Using the Sogni spatula, collect a small quantity of product on the desired border of the spatula and apply to the wall in swift, crossed motions of the spatula to form the typical embossed pattern.



**Thinning:** Ready to use or with max. 5% water

### Technical data:

Spread rate (per coat of Sogni SK, applied as described):	
Stippled effect.....	4 ÷ 6 sq.m./litre
Spatula effect .....	12 ÷ 14 sq.m./litre
Drying time at 25°C: .....	4 ÷ 6 hours
Recoat time: .....	12 ÷ 18 hours
Specific gravity: .....	1040 ± 10 g/l
Viscosity (Brookfield, 20°C): .....	4500 ÷ 6000 mPa.s
Solid contents (%): .....	25 ± 2
V.O.C. (EC norm 2004/42/CE) .....	90 g/l (Cat. L BA from 2010 max value: 200 g/l)



### Advices:

Do not apply with air and surface temperatures below 5°C or above 28°C. Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working process, and reducing the risk of differences in tones. It is also advisable to mix together the product when using different lots and multiple cans for the same job. Clean tools with warm water. Store the product well protected from freezing and excess heat.

*Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.*